

PRODUCT DESCRIPTION

TREMproof Façade is a high performance, water based acrylic coating designed to provide a decorative and protective façade coating. TREMproof Façade is a single component, highly flexible, waterproof protective coating, which provides an aesthetically pleasing finish.

USAGE/PURPOSE

TREMproof Façade has been designed to be used on:

- Façades
- Columns
- Partitioning
- Brick/Masonry/Rendered Walls

FEATURES & BENEFITS

- Excellent resistance to UV and weathering.
- Extremely durable and flexible.
- Excellent adhesion to prepared substrates.
- Dirt pick-up resistance and easy to maintain.
- Environmentally friendly.
- Colour matching available.

PACKAGING

15L Pail

COLOURS (Satin Finish Only)

Standard colour range – White, Mid Grey & Sandstone

**Whilst care is taken to accurately colour match, batch to batch variations may occur. Tremco strongly suggest project requirements are ordered in a single batch lot to avoid potential colour matching variations. Minimum order quantities and charges may apply.*

SHELF LIFE

6 months when stored as recommended in original unopened packaging.

STORAGE

Store in original, undamaged packaging in a clean, dry, protected location.

LIMITATIONS

- Do not apply onto damp or contaminated substrates.
- Not to be used as a trafficable coating.
- Do not apply coating onto hot substrates.
- Do not apply if rain is imminent, within 12 hours after application.

COVERAGE RATE

4.5m²/L (per coat)

DFT – 0.25 mil

CONCRETE SURFACE PREPARATION

1. Surface must be clean, sound, dry, free from dust, debris, loose materials or contaminants which may contribute to adhesion issues. Existing coatings may also need to be totally removed. A stiff brush, scraper or mechanical grinding may be required.
2. Surface divots and imperfections will need to be addressed by way of surface re-profiling to create a uniform substrate. TREMcrete HB Ultra should be considered for deeper imperfections – please seek technical advice from a Tremco representative.



MOVEMENT JOINTS & EXISTING CRACKS

1. TREMproof Façade should not be applied directly over movement joints as this may exceed the movement capability of the coating. All joints need to be prepared and sealed with an appropriate sealant such as Tremco's Dymonic 100 - please seek technical advice from a Tremco representative.
2. Cracks should be addressed and prepared accordingly with an appropriate bandage system such as Tremco's Permafab or sealant such as Tremco's Dymonic 100 - please seek technical advice from a Tremco representative.
3. It is highly recommended to avoid applying polyurethane sealants as this may cause bleeding into the coating being applied.

PRIMING

- Tremco suggest applying either TREMproof WB Primer or TREMproof 200EC onto the prepared substrate. When using TREMproof WB Primer, allow 2 – 4 hours before applying the coating. When using TREMproof 200EC, allow 4 – 6 hours before applying the coating.
- Primer drying times may vary depending on ambient conditions.

MIXING INSTRUCTIONS

TREMproof Façade should be mixed with a suitable electric paddle mixer at a rate of 500rpm for a minimum of 3 minutes, ensuring there is no settlement at the base of the drum.

APPLICATION INSTRUCTIONS

1. TREMproof Façade can be applied by roller, brush or airless spray. Dependent on the aesthetic finish required, a nap roller or textured roller can be used. The coating is to be applied evenly at the recommended coverage rates.
2. First coat application is to achieve a wet film thickness of no less than 215 microns. After allowing the first coat to dry between 6 – 8 hours, a second can be applied at the same wet film thickness (215 microns).
3. Drying times may vary depending on ambient conditions.

CLEAN UP

- Clean all adjacent areas to remove any stains or spills with Tremco Xylo.
- Clean tools or equipment with Tremco Xylo before material cures.

HEALTH & SAFETY PRECAUTIONS

The Safety Data Sheet (SDS) must be read and understood prior to use.

TECHNICAL SERVICE

Tremco CPG Australia Pty Ltd has a team of Representatives who provide assistance in the selection and specification of products. For more detailed information or service and advice, call Customer Service on (02) 9638 2755 or fax (02) 9638 2955.

GUARANTEE/WARRANTY

Tremco CPG Australia Pty Ltd products are manufactured to rigid standards of quality. Any product which has been applied (a) in accordance with Tremco CPG Australia written instructions and (b) in any application recommended by Tremco CPG Australia, but which is proved to be defective, will be replaced free of charge.

Any information provided by Tremco CPG Australia in this document in relation to Tremco CPG Australia's goods or their use is given in good faith and is believed by Tremco CPG Australia to be appropriate and reliable. However, the information is provided as a guide only, as the actual use and application will vary with application conditions which are beyond our control. Tremco CPG Australia makes no representation, guarantee or warranty relating to the accuracy or reliability of the information and assumes no obligation or liability in connection with the information. To the extent permitted by law, all warranties, expressed or implied are excluded.

CONTACT OUR TEAM

Tremco CPG Australia Pty Ltd

ABN: 25 000 024 064

Unit 12, 4 Southridge Street

Eastern Creek, NSW 2766

P: (02) 9638 2755

F: (02) 9638 2955

E: tremco@tremco.com.au